

ASHLAR

FOND DU LAC RUSTIC



GEOLOGY: dolomitic limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

brown, buff,
tan, and gold

COLOR CONSISTENCY PER PALLET

consistent

WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$ (inches cubed) $\times 170$
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds

THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
36 square feet / ton	26 ft ² /ton	46 ft ² /ton

FOND DU LAC RUSTIC

DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 6" to 42" (16") l: 152 to 1066 (406)

h: 1/2" to 8" h: 50 to 152

w: 3" to 5" (4") w: 76 to 127 (101)

sides of stone shall be no less than 2-1/2
inches in width; stone shall not vary in height
more than a 1/4 of an inch in a 12 inch span

EXAMPLE

a stone that is 24 inches long could have a
height of 6 inches on one end and 5-1/2
inches on the other end and be acceptable

TYPICAL PIECE

ends square;
natural cleft top and bottom;
weatheredge and seamface face;
split back; sides either split
or naturally square;
stone is mostly rectangular

PART NUMBERS

FULL VENEER

part number: 1BSTBUE02001TN

THIN VENEER

qty bx flat: 1BTVBUE02001QB

sm bx flat: 1BTVBUE02001BX

qty bx corner: 1BTVBUE02501QB

sm bx corner: 1BTVBUE02501BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

FOND DU LAC RUSTIC

DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 6" to 24" (12") l: 152 to 533 (304)

h: 1/2" to 8" h: 12 to 203

w: 3/4" to 1-1/4" (1") w: 19 to 31 (25)

corner return 3" to 5" cr: 76 to 127

stone shall not vary in height more than a 1/4
of an inch in a 12 inch span

EXAMPLE

a stone that is 24 inches long could have a
height of 6 inches on one end and 5-1/2
inches on the other end and be acceptable

TYPICAL PIECE

ends square;
natural cleft top and bottom;
weatheredge and seamface face;
sawn back; sides either split or
naturally square;
stone is mostly rectangular

ASTM TESTING DATA

FOND DU LAC C97 water absorption—0.36%

FOND DU LAC C97 density—174.2 pcf

FOND DU LAC C99

modulus of rupture—1,470 psi

FOND DU LAC C170

compressive strength w/rift—29,040 psi

compressive strength across rift—34,240 psi

FOND DU LAC C880

flexural strength—1,740 psi



www.buechelstone.com